

CE



Gleeson Precast
Golden, Co Tipperary

13

IS EN 13242:2002+A1:2008
Aggregates for hydraulically bound and
Unbound Materials
Crusher Run

Particle Shape	FI21
Particle Size	
Particle Density	2.63Mg/m ³
Fines Content	F2
Resistance to fragmentation/crushing	LA22
Resistance to polishing	PSV43
Resistance to abrasion	AAV3.9
Resistance to wear	Mde 15
Composition/content	
Chlorides	C <0.01%
Acid Soluble Sulphates	AS 0.1%
Total Sulphur	TS 0.1%
Volume Stability	
Dry Shrinkage	0.027%
Water Absorption	WA 0.4%
Emission of Radioactivity	NA
Release of heavy metals	NA
Release of polyaromatic hydrocarbons	NA
Release of any other dangerous substances	NA